



## ARPRO<sup>®</sup> Product Listing Expanded Polypropylene (EPP) Standard Grade<sup>1</sup>

## **BULK DENSITY SPECIFICATION**

## <u>Black</u>

## <u>White</u>

Dreduct	Density, grams/liter (g/l)		
Product Type	Lower Limit	Nominal	Upper Limit
5012	12.8	14.4	15.8
5013	14.4	16.2	18.0
5015	18.0	20.0	22.0
5017	21.0	23.0	25.0
5018	22.0	24.0	26.0
5019	23.5	26.1	28.7
5022	25.0	27.5	30.0
5025	26.0	29.0	32.0
5027	31.0	34.0	37.0
5028	32.5	35.3	38.1
5029	35.0	38.0	41.0
5030	38.4	41.7	45.0
5035	41.0	45.0	49.0
5037	44.3	48.1	52.0
5040	46.0	50.0	54.0
5042	48.7	52.9	57.2
5046	54.6	59.3	64.1
5050	60.5	65.8	71.0
5052	64.5	70.0	75.5
5053	68.0	74.0	80.0
5056	73.4	79.8	86.1
5060	76.5	85.0	93.5
5062	79.4	88.2	97.0

Dreduct	Density, grams/liter (g/l)		
Product Type <sup>2</sup>	Lower Limit	Nominal	Upper Limit
0040/0440	40.0		45.0
3012/3412	12.8	14.4	15.8
3013/3413	14.4	16.2	18.0
3015/3415	18.0	20.0	22.0
3017/3417	21.0	23.0	25.0
3019/3419	23.5	26.1	28.7
3025/3425	26.0	29.0	32.0
3027/3427	31.0	34.0	37.0
3028/3428	32.5	35.3	38.1
3029/3429	35.0	38.0	41.0
3030/3430	38.4	41.7	45.0
3037/3437	44.3	48.1	52.0
3042/3442	48.7	52.9	57.2
3046/3446	54.6	59.3	64.1
3050/3450	60.5	65.8	71.0
3053/3453	68.0	74.0	80.0

<sup>1</sup>Note: Certain product grades may be limited to specific JSP Plant locations. Contact JSP for details. JSP Standard grade product is a small bead. Details of approximate dimensional size are available.

<sup>2</sup>Note: 34XX (White) grades are slightly larger bead size vs. 30XX grades and are available at select JSP locations.

ARPRO® is a registered trademark of JSP International Group, Ltd. PUBLICATION: techdoc\_StandardGradeList\_ARPRO-EPP\_2018

The information contained herein is based upon the results of limited laboratory tests on test samples of material molded from expanded polyolefin resin manufactured by JSP. There can be no assurance that the similar results will be achieved in simulated tests or actual use of commercial product molded by customers of JSP. Product performance may vary substantially depending upon the particular application or processing involved. The listed properties are illustrative only and not the product specifications. All suggestions and recommendations are made without warranty since the conditions of use are beyond JSP's control. Processing and applications of JSP form products can influence molded part performance in many ways. Consequently, processors and/or users are advised that there may be aneed to conduct independent tests and experiments in order for them to determine the extent to which they may choose to rely upon such information in their business operations. JSP disclaims any liability in connection with the use of the information and does not warrant against infringement by reasons of the use of its products in combination with other material or in any process.

