



ARPRO[®] Product Listing Expanded Polypropylene (EPP) Recycled Content Grade Made with a Minimum of 30% Recycled Content¹

BULK DENSITY SPECIFICATION

Dreduct	Density, grams/liter (g/l)		
Product Type	Lower Limit	Nominal	Upper Limit
5015RC	17.6	20.0	22.4
5017RC	20.2	23.0	25.8
5019RC	23.0	26.1	29.2
5025RC	25.5	29.0	32.5
5027RC	30.6	34.0	37.4
5029RC	34.2	38.0	41.8
5030RC	37.5	41.7	45.9
5037RC	43.3	48.1	52.9
5042RC	47.6	52.9	58.2
5046RC	53.4	59.3	65.2

¹Note: 50XXRC Series product grades are limited to specific JSP Plant locations. Contact JSP for details.



ARPRO[®] 50XXRC Black EPP products contain a minimum of 30% Post Consumer Recycled (PCR) content sourced from End-Of-Life molded EPP parts and/or Post Industrial Recycled (PIR) content sourced from EPP Industry Molding Scrap and/or Fabrication Offal. The production of this product contributes to the reduction of CO₂ emissions by 15% (~13 to 15%) compared to standard ARPRO[®] 50XX Black EPP products. Contact your JSP Sales Representative for product and grade availability.

ARPRO® is a registered trademark of JSP International Group, Ltd. PUBLICATION JSP-techdoc--RecycledContentEPP(50XXRC)GradeList-2023-2

The information contained herein is based upon the results of limited laboratory tests on test samples of material molded from expanded polyolefin resin manufactured by JSP. There can be no assurance that the similar results will be achieved in simulated tests or actual use of commercial product molded by outsomers of JSP. Product performance may vary substantially depending upon the particular application or processing involved. The listed properties are illustrative only and not the product specifications. All suggestions and recommendations are made without warranty since the conditions of use are beyond JSP's control. Processing and applications of JSP foam products can influence molded part performance in many ways. Consequently, processors and/or users are advised that there may be a need to conduct independent tests and experiments in order for them to determine the extent to which they may choose to rely upon such information in their business operations. JSP isolations with other material or in anv orccess.

